

The science and art of ultrafast laser writing

P. G. Kazansky

Optoelectronics Research Centre, University of Southampton, SO17 1BJ, UK
pgk@orc.soton.ac.uk

Femtosecond laser writing in transparent materials has attracted considerable interest due to new science and a wide range of applications from laser surgery, 3D integrated optics and optofluidics to optical data storage [1]. Two decades ago it was discovered that under certain irradiation conditions subwavelength periodic structures with record small features of 20 nm, can self-organize in the volume of fused quartz [2-4]. On the macroscopic scale the self-assembled nanostructure behaves as a uniaxial crystal with negative birefringence. The control of the polarization azimuth allows direct writing of flat optics elements with spatially variant anisotropy, which exploits the geometrical or Pancharatnam-Berry phase and in particular S-waveplates for polarization shaping (Fig. 1a) [5]. The applications of S-waveplates ranges from material processing and optical trapping to extreme UV generation [6].




Fig. 1. (a) Femtosecond laser written S-waveplate in cross-polarized light. (b) 5 D optical storage. Each voxel contains a self-assembled nanograting oriented perpendicular to the light polarization. (c) Eternal copy of King James Bible imprinted in silica glass.

More recently ultralow-loss birefringent optical elements including UV retarders and geometrical phase lenses and prisms have been demonstrated exploiting new type of anisotropic nanoporous modification in glass, referred to as Type X [7].

A remarkable phenomenon was also discovered, referred to as quill or calligraphic laser writing, which reveals strong dependence of the material modification, in particular the self-assembled nanostructures, on the writing direction relative to the pulse front tilt [8]. Moreover, coupling of polarization with the angular dispersion, has been demonstrated as a new degree of freedom in ultrafast laser material processing [9].

It was also explored for the optical data storage in the bulk of silica glass, in addition to three spatial coordinates, using two independent parameters of induced form birefringence, the slow axis orientation (4th dimension) and the strength of retardance (5th dimension) (Fig. 1b). The slow axis orientation and retardance can be independently controlled by the polarization and intensity of the femtosecond laser beam. The data optically encoded into five dimensions can be successfully retrieved by quantitative birefringence measurements. The storage allows hundreds of terabytes per disc data capacity and thermal stability up to 1000° and is vital step towards an internal archive (Fig. 1c) [10]. Project Silica is exploiting 5D optical storage in glass for the first-ever storage technology designed and built from the media up, for the cloud [11].

[1] R. R. Gattas and E. Mazur, "Femtosecond laser micromachining in transparent materials," *Nature Photonics* **2**, 219 (2008).

[2] P. G. Kazansky, H. Inouye, T. Mitsuyu, K. Miura, J. Qiu, K. Hirao and F. Starrost, "Anomalous anisotropic light scattering in Ge-doped silica glass," *Phys. Rev. Lett.*, **82**, 2199 (1999).

[3] J. D. Mills et al., "Embedded anisotropic microreflectors by femtosecond-laser nanomachining," *Appl. Phys. Lett.* **81**, 196 (2002)

[4] Y. Shimotsuma et al., "Self-organized nanogratings in glass irradiated by ultrashort light pulses," *Phys. Rev. Lett.* **91**, 247705 (2003).

[5] M. Beresna, M. Gecevicius and P. G. Kazansky, "Ultrafast laser direct writing and nanostructuring in transparent materials," *Advances in Optics and Photonics* **6**, 293 (2014).

[6] C. Hernández-García, et al., Extreme ultraviolet vector beams driven by infrared lasers, *Optica*, **5**, 520 (2017).

[7] Y. Lei, M. Sakakura, L. Wang, Y. Yu, R. Drevinskis and P. G. Kazansky, "Low-loss geometrical phase elements by ultrafast laser writing in silica glass", *CLEO, OSA Technical Digest (Optical Society of America, 2019)*, paper ATu4I.4.

[8] P. G. Kazansky et al., "Quill" writing with ultrashort light pulses in transparent materials," *Appl. Phys. Lett.* **90**, 151120 (2007).

[9] A. Patel, V. T. Tikhonchuk, J. Zhang and P. G. Kazansky, "Non-paraxial polarization spatio-temporal coupling in ultrafast laser material processing", *Laser & Photonics Reviews* **11** (3) (2017).

[10] J. Zhang et al., "Seemingly unlimited lifetime data storage in nanostructured glass," *Phys. Rev. Lett.* **112**, 033901 (2014); <https://www.archmission.org/>

[11] <https://www.microsoft.com/en-us/research/project-silica/>